

CONCRETE POLISH PROCESS

Seal all Cracks and joints with Clear Polyurea PE-85 (two part) to specifications.

30 grit metal pad

70 grit metal pad

120 Grit metal pad

Wash

Consolideck LS (hardener) saturation

100 Grit Resin Pads

200 grit Resin Pad

400 grit Resin Pad

800 grit resin Pad

Wash

Consolideck LS Guard (Sealer) Saturation

Buff Pass with 800 grit Resin Pad

Buff Pass with 3000 Grit Pad